

DEC 04 2007

Application No.: 10/591,178Docket No.: 4590-556**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions and listings of claims in the application:

Listing of Claims:

1. (Currently Amended) A method for fabricating a reading diode (DL) of small dimensions between two silicon electrodes deposited above a substrate, said electrodes being a last electrode of a CCD shift register and a reset electrode for emptying electrical charges received by the reading diode from the shift register, comprising the following steps:

- a) producing the two electrodes, separated by a gap, above the substrate;
- b) thermally oxidizing a part of a thickness of the electrodes, in height and in width, leaving a space remaining between the oxidized electrodes, the substrate being protected against oxidation in the space;
- c) exposing the surface of the substrate in the space,
- d) depositing a layer of doped polycrystalline silicon entering in contact with the substrate in the space in order to form one pole of the diode, the substrate forming another pole,
- e) partially removing the polycrystalline silicon while leaving a desired pattern remaining, the pattern covering at least the space left between the electrodes and also covering a region lying outside the space,
- f) depositing an insulating layer, and locally etching an opening into the insulating layer above the polycrystalline silicon outside the space lying between the electrodes, in order to form an offset contact zone, depositing a metal layer entering in contact with the polycrystalline silicon in the offset contact zone, and etching the metal layer according to a desired pattern of interconnections.

Application No.: 10/591,178**Docket No.: 4590-556**

2. (Currently Amended) The method as claimed in claim 1, wherein step e) includes: depositing a uniform layer of silicon nitride and etching according to a pattern which leaves the layer remaining above the polycrystalline silicon zones that are intended to be kept, and the silicon is subsequently oxidized over its entire thickness wherever it is not covered with nitride, until a silicon pattern is obtained which comprises only the zones that were ~~[[not]]~~ covered with nitride.

3. (Previously Presented) The method as claimed in claim 2, wherein between the deposition of the nitride layer and the subsequent step of oxidizing the polycrystalline silicon, the polycrystalline silicon is chemically attacked in order to remove it as much as possible wherever it is not protected by the nitride.

4. (Currently Amended) An integrated circuit comprising:

a CCD register with a readout diode at the end of the register, between ~~[[the]]~~ a last electrode of the register and a reset electrode for emptying electrical charges received by the reading diode, wherein the readout diode includes a doped region delimited on one side by the electrodes and on the other side by regions of thick silicon oxide, the doped region being entirely covered with a layer of polycrystalline silicon delimited according to a pattern which extends partly above the thick oxide, the silicon layer being covered with an insulating layer having an opening above the thick oxide but no opening above the doped region, and the insulating layer being itself covered with a conductive layer entering in contact with the polycrystalline silicon through the opening.

5. (Currently Amended) The integrated circuit as claimed in claim 4, wherein the polycrystalline silicon layer is covered with silicon nitride, itself covered by the insulating layer, the nitride layer having the same pattern as the polycrystalline silicon and, ~~[[also]]~~ being open at the position of the opening in the insulating layer.